

## AVISTA peer EVO ATF 3000

High-grade automatic transmission oil of the AVISTA peer EVO line meeting the Dexron III-H specification, as well as many OEM approvals. The product is field-tested for application where Dexron II and GM Motors Type A Suffix A (TASA) is recommended.

### APPLICATION

- Automatic transmissions
- The product is red coloured.

### CHARACTERISTICS / APPLICATION BENEFITS

- High-stable viscosity index
- very low flow point
- very good oxidation stability
- well adapted friction coefficients
- neutral behaviour by inhibition to non-ferrous metals

### APPROVALS

<b>DTFR</b>	13C170 (MB 236.9) 13C100 (MB 236.1)
<b>MAN</b>	MAN 339 Typ L-1 / V-1 / Z-1
<b>ZF</b>	ZF TE-ML 03D, 04D, 14A, 17C (ZF004774)

### SPECIFICATIONS

<b>GM</b>	Dexron III-H
<b>Ford</b>	Mercon
<b>Voith</b>	55.6335.xx

### RECOMMENDATIONS

<b>Allison</b>	C-4 TES-389
<b>Caterpillar</b>	TO-2
<b>Renk Doromat</b>	Renk Doromat
<b>Volvo</b>	97341
<b>ZF</b>	ZF TE-ML 11B

### TYPICAL CHARACTERISTICS

(The given data are typical data.)

Parameter	Method	Unit	
SAE Class	SAE J 306		75W
Density @ 15 °C	DIN EN ISO 12185	g/cm <sup>3</sup>	0.830 – 0.870
Kin. Viscosity @ 40 °C	ASTM D7279	mm <sup>2</sup> /s	29 - 47
Kin. Viscosity @ 100 °C	ASTM D7279	mm <sup>2</sup> /s	7.2 – 8.7
Viscosity Index	ASTM D2270		min. 175
Brookfield @ -40 °C	DIN 51398	mPa*s	max. 20.000
Flash Point COC	DIN ISO 2592	°C	min. 200
Pour Point	ASTM D7346	°C	max. -54

We reserve the right to change the general characteristics of our product so that our customers can benefit from the latest technological advances. (VS-Number 12)